



中国认可
国际互认
检测
TESTING
CNAS L2021



CEMT/QR-7.8-01-03-2020(1)

共 11 页 第 1 页/ page 1 of 11

No: 202303156

检测报告

TEST REPORT

产品名称

Name of sample:

3242环氧玻璃布层压板
3242 Epoxy Glass Cloth Laminated Sheet

委托单位

Client:

九江鑫星绝缘材料有限公司
JIU JIANG XIN XING INSULATION
MATERIAL CO.,LTD

检测类别

Classification of test:

日常委托
Commission test

桂林赛盟检测技术有限公司
机械工业电工材料产品质量监督检测中心

Guilin CEMT Technology Co., Ltd.

Electrical Materials Quality Supervision and
Testing Center of Machinery Industry of China

声 明

1. 本检测报告（包括复印件）无“检验专用章”一律无效。
2. 本检测报告部分复制无效。
3. 本检测报告无主检、审核、批准人签名无效。
4. 本检测报告涂改无效。
5. 检测结果仅适用于收到的委托检测样品。
6. 本检测报告若无CMA标识，表明其数据和结果在中华人民共和国境内仅供内部参考，不具有证明作用。

桂林赛盟检测技术有限公司
机械工业电工材料产品质量监督检测中心
地址：中国广西桂林市七星区东城路8号
邮编：541004

电话：0773-5603029、5888294、5888408
传真：0773-5603029

E-mail: postmaster@cemt.org.cn
网址: www.cemt.org.cn

Declaration

1. This test report (including copy) is invalid if it is without the "Test Stamp".
2. The partial copy of this test report is invalid.
3. This test report is invalid without all the signatures of the chief surveyor, auditor and approver.
4. This test report is invalid if it is with any altering and rasure.
5. The test results shown this test report relate only to the received samples provided by the client.
6. In China, if this test report without CMA identification, it indicates that the data and results are only for the internal reference, no any social proof effect.

Guilin CEMT Technology Co., Ltd.
Electrical Materials Quality Supervision and Testing Center of Machinery Industry of China

Address: No.8 Dongcheng Road, Qixing District, Guilin City, Guangxi, China
PC: 541004

Tel: (0086) 773-5603029、5888294、5888408

Fax: (0086) 773-5603029

E-mail: postmaster@cemt.org.cn

http: // www. cemt.org.cn

检测报告

TEST REPORT

产品名称 Name of sample	3242环氧玻璃布层压板 3242 Epoxy Glass Cloth Laminated Sheet		
型号 Type	—	规格 Specifications	—
批号和/或生产日期 Lot and/or Manufacture No.	—	商标 Trademark	—
委托单位 Client	九江鑫星绝缘材料有限公司 地址: 江西省九江市濂溪区濂溪大道2号 JIU JIANG XIN XING INSULATION MATERIAL CO.,LTD Add:No.2 Lianxi Road,Lianxi District,Jiujiang City,Jiangxi Province,China 联系人/Contact: 骆训华/Xunhua Luo 电话/Tel: (0086)18970279478 邮箱/E-mail: 8160890@qq.com		
生产单位 Manufacturer	—		
以上信息及样品由委托方提供及确认, CEMT不承担证实委托方提供信息的准确性、适当性和(或)完整性的责任。 The above information and samples are provided and confirmed by the client. CEMT shall not be responsible for verifying the accuracy, appropriateness and/or completeness of the information provided by the client.			
接收样品状态 Received sample status	按标准要求制备的试样/Standard sample		
接样日期 Received sample date	2023-05-16	完成日期 Test completion date	2023-05-30
检测方法 Test method	GB/T 1303.2-2009等/etc.		
检测结论/Test conclusions: 来样经检测, 仅给出实测值。 A sample of the product was tested, and the test results are only given the measured values.			
主检: Chief surveyor:	刘发远	审核: Auditor:	周雨力
		签发日期: Issue Date:	2023-06-01
		批准: Approved by:	于志英

检测报告

TEST REPORT

产品名称/Name of sample : 3242环氧玻璃布层压板/3242 Epoxy Glass Cloth Laminated Sheet

序号 Item	检测性能/项目 Property	单位 Unit	要求 Requirement	检测结果 Test result	检测方法 Test method
1	垂直层向弯曲强度 (常态, 纵向) Flexural strength perpendicular to laminations(Normality,MD)	MPa	—	639	GB/T 1303.2-2009
2	垂直层向弯曲强度 (155℃±2℃, 纵向) Flexural strength perpendicular to laminations(155℃±2℃,MD)	MPa	—	432	
3	平行层向简支梁冲击强度 (缺口, 纵向) Charpy impact strength parallel to laminations (Notched,MD)	kJ/m ²	—	105	
4	拉伸强度 (纵向) Tensile strength(MD)	MPa	—	460	
5	垂直层向电气强度 (90℃±2℃, 25#变压器油中, 20s逐级升压, Φ25mm/Φ75mm圆柱电极) Electric strength perpendicular to laminations (at 90℃±2℃ in 25# transformer oil,20s step-by-step test,Φ25mm/Φ75mm cylindrical electrode)	kV/mm	—	21.9	
6	平行层向击穿电压 (90℃±2℃, 25#变压器油中, 20s逐级升压, Φ130mm/Φ130mm平板电极) Breakdown voltage parallel to laminations(at 90℃±2℃ in 25# transformer oil,20s step-by-step test,Φ130mm/Φ130mm plate electrode)	kV	—	> 100	
7	相对电容率 (1MHz) Relative Permittivity(1MHz)	—	—	4.87	
8	绝缘电阻 (锥销电极, 电极间距25mm) Insulation resistance(Using taper pin electrodes, and the electrode spacing is 25.0 mm)	Ω	—	3.2×10 ¹³	

检测报告

TEST REPORT

产品名称/Name of sample : 3242环氧玻璃布层压板/3242 Epoxy Glass Cloth Laminated Sheet

序号 Item	检测性能/项目 Property	单位 Unit	要求 Requirement	检测结果 Test result	检测方法 Test method
9	绝缘电阻 (浸水24h后, 锥销电极, 电极间距25mm) Insulation resistance(After 24h immersion in water, using taper pin electrodes, and the electrode spacing is 25.0 mm)	Ω	—	8.0×10^{12}	GB/T 1303.2-2009
10	相比电痕化指数 (CTI600) Comparative tracking index(CTI600)	—	—	CTI600	
11	密度 Density	g/cm^3	—	1.83	
12	粘合强度 Adhesion strength	N	—	8053	GB/T 1303.6-2009中规定的试验方法 The methods specified in GB/T 1303.6-2009
13	玻璃化转变温度 (DSC法) Glass transition temperature(DSC method)	$^{\circ}\text{C}$	—	175	GB/T 22567-2008

备注/Remark:

- 第5项“垂直层向电气强度”试验试样的厚度为 (1.08~1.11) mm;
The thickness of the specimens for Item 5 “Electric strength perpendicular to laminations” test are (1.08~1.11)mm.
- 第6项“平行层向击穿电压”试验试样的尺寸为 (100.20~100.46) mm (长) × (25.07~25.30) mm (宽) × (10.35~10.36) mm (厚), 电极间距为 (25.07~25.30) mm;
The sizes of the specimens for Item 6 “Breakdown voltage parallel to laminations” test are (100.20~100.46)mm (length)×(25.07~25.30)mm (width)×(10.35~10.36)mm (thickness). And the electrode spacing is (25.07~25.30)mm.
- 第12项“粘合强度”试验试样的尺寸为 (24.91~25.04) mm × (24.97~25.11) mm × (10.72~10.76) mm;
The sizes of the specimens for Item 12 “Adhesion strength” test are (24.91~25.04)mm×(24.97~25.11) mm×(10.72~10.76)mm.
- 试验过程照片见图1~图10。
The pictures of the tests are shown in Fig.1~Fig.10.

检测报告

TEST REPORT

产品名称/Name of sample : 3242环氧玻璃布层压板/3242 Epoxy Glass Cloth Laminated Sheet





图1 垂直层向弯曲强度试验
Fig.1 Flexural strength perpendicular to laminations test

检测报告 TEST REPORT

产品名称/Name of sample : 3242环氧玻璃布层压板/3242 Epoxy Glass Cloth Laminated Sheet




图2 平行层向简支梁冲击强度（缺口，纵向）试验
Fig.2 Charpy impact strength parallel to laminations (Notched,MD) test



图3 拉伸强度（纵向）试验
Fig.3 Tensile strength(MD) test




图4 垂直层向电气强度试验
Fig.4 Electric strength perpendicular to laminations test




图5 平行层向击穿电压试验
Fig.5 Breakdown voltage parallel to laminations test

检测报告 TEST REPORT

产品名称/Name of sample : 3242环氧玻璃布层压板/3242 Epoxy Glass Cloth Laminated Sheet



图6 相对电容率试验
Fig.6 Relative Permittivity test




图7 绝缘电阻试验
Fig.7 Insulation resistance test

检测报告

TEST REPORT

产品名称/Name of sample : 3242环氧玻璃布层压板/3242 Epoxy Glass Cloth Laminated Sheet




图8 相比电痕化指数试验
Fig.8 Comparative tracking index test





图9 粘合强度试验
Fig.9 Adhesion strength test

检测报告

TEST REPORT

产品名称/Name of sample : 3242环氧玻璃布层压板/3242 Epoxy Glass Cloth Laminated Sheet




图10 玻璃化转变温度曲线
Fig.10 Glass transition temperature curve

以下空白/End of report

